

Our Ref: SW/PN/BR

25 September 2013

Report 207881

Page 1 of 3

Camira
Hopton Mills
Mirfield
West Yorkshire
WF14 8HE

Contact: David Brook

DATE RECEIVED	:	19 SEPTEMBER 2013
FABRIC SUPPLIER	:	ANTEX
QUALITY/REFERENCE	:	NEXUS
REPUTED FIBRE CONTENT	:	NOT GIVEN
FABRIC DESCRIPTION	:	KNITTED
COLOUR/DESIGN	:	LIMESTONE
END USE	:	SCREEN
STYLE NUMBER	:	HUNY02 168256 0106
ORDER NUMBER	:	45910
PERFORMANCE STANDARD	:	GENERAL

REQUEST: BS7176:2007 + A1:2011 Specification for resistance to ignition of upholstered furniture for non-domestic seating by testing composites – Table 1: Low Hazard Use

COMMENTS: Meets the flammability performance requirements of BS7176:2007 + A1:2011 -Table 1 Low Hazard Use



S. WISEMAN
LABORATORY DIRECTOR



P. NEESAM
HEAD OF FLAMMABILITY

This report shall not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.

BS 7176:2007 + A1:2011 Specification for resistance to ignition of upholstered furniture for non-domestic seating by testing composites

BS7176:2007 +A1:2011 specifies flammability performance requirements for composites comprising cover fabric and filling material(s) and includes additional requirements in clause 4.1.2 relating to the flammability behaviour of the filling materials used. The filling materials which will be used in the final article are not always known to the fabric supplier and therefore nominal filling materials are used for the purpose of testing which may not necessarily represent the final composite. All filling materials supplied by HSTTS for the purpose of testing cover fabrics comply with the relevant requirements of clause 4.1.2.

Clause 4.1.1 requires that testing is carried out in accordance with the frequency stated in clause 5. No information was provided by the client regarding the lot size or frequency of testing.

According to Table 1, composites for Low Hazard end-use shall meet the requirements of BSEN 1021-1:2006 (cigarette ignition source) and BSEN 1021-2:2006 (match-equivalent flame).

Pre-treatment:

In accordance with clause 4.2, all fabrics which have been chemically treated to reduce their ignitability are subjected to the water soaking and drying procedures specified in BS 5852:2006 Annex E prior to being conditioned. Such pre-treatment is not necessary for materials which are formulated to be or are inherently flame-retarded.

Pre-treatment applied: BS 5852:2006 Annex E

Conditioning

After any pre-treatment given but prior to testing, the test specimens of fabric, Ref: Nexus were subjected to conditioning for at least 72 hours in ambient indoor conditions followed by a minimum of 24 hours at a temperature of (23± 2°C) and relative humidity of (50±5%).

Test results

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use. They also only relate to the materials tested. They do not guarantee to represent the performance of production materials.

Filling material used: Combustion modified high resilience foam infill of approximately 36 kg/m³.

- (i) BS EN 1021-1:2006 Furniture - Assessment of the ignitability of upholstered furniture – Part I.
Ignition Source: Smouldering cigarette.

<u>Test</u>	<u>Observations</u>	<u>Outcome</u>
1	No flaming or progressive smouldering observed	NI (Non-ignition)
2	No flaming or progressive smouldering observed	NI (Non-ignition)

Our Ref: SW/PN/BR

25 September 2013

Report 207881

Page 3 of 3

- (ii) BS EN 1021-2:2006 Furniture - Assessment of the ignitability of upholstered furniture – Part 2. Ignition Source Match flame equivalent.

Duration of flame application: 15 seconds

<u>Test</u>	<u>Observations</u>	<u>Outcome</u>
1	Duration of flaming: 2 secs No progressive smouldering observed	NI (Non-ignition)
2	Duration of flaming: 1 secs No progressive smouldering observed	NI (Non-ignition)
3	Duration of flaming: 2 secs No progressive smouldering observed	NI (Non-ignition)

Comments

Meets the flammability performance requirements of BS7176:2007 + A1:2011 -Table 1 Low Hazard Use